

INSTALLATION TIPS

POOL COPING



DISCLAIMER

Please note, all the information provided in this document should only be used as a guide at the time of installation for trade practices only.

All information offered is in conjunction with site-specific factors. Kindly note, the guide and the provided instructions are not intended to replace any expert contractors' or consultants' advice or the applicable manufacturer's technical data sheet or suggested application method.

Any information in this document may be changed, deleted, or otherwise modified by Stone Centre without prior notice basis business requirements.

PRODUCT CONSIDERATIONS

Stone Centre's range of Pool Coping products are made of natural stones and because of their age-long development under a variety of weather conditions, these pavers will vary from batch to batch. A significant part of what everyone loves about natural stones is the natural variation that makes them so distinctively lovely.

It is normal to anticipate some degree of dimension and thickness tolerance. Samples should only be used as a guide for shade and colour. Stone Centre advises you to evaluate the product at the time of delivery to make sure the stone's colour and other qualities are as per your expectations. During installation, always ensure to combine pavers and tiles equally from all crates.

Minor scuffing and marks are not regarded as structural defects. Kindly notify Stone Centre Team before the installation, if there is any noticeable severe chipping or thickness variance in the provided product, if any. The product is accepted before installation only.

THICKNESS/SIZE CONSIDERATIONS

The Buyer should keep in mind, some 1st-grade pool coping may be slightly chipped and/or broken. These imperfections can be used as cuts/infill. All stone pavers and tiles may vary in dimensions by +/-2mm when sawn cut and the thickness may vary by +/-3mm. respectively.

STORAGE

The product should ideally be kept indoors, away from rain and direct sunlight. Kindly avoid stacking crates on top of one another.

INSTALLATION CONSIDERATIONS FOR POOL COPING

CONTROL JOINTS

It is advised to use control joints on the substrate (concrete subbase). The mortar bed and grout joint should match the joints in the concrete base. Temperature changes and other movements in the subgrade, concrete base, mortar, or actual tile itself can produce variances in the flooring, which are helped by control joints. Every 20m², tiled surfaces should also have adequate control joints that extend through the tile and the bedding mix but not through the concrete substrate, in addition to structural concrete joints. Technical expansion joints are typically laid out in transverse and/or longitudinal directions in compartments within the overall floor field (minimum 5mm joints every five meters). Control joints will significantly lower the likelihood of unattractive surface cracks developing.

DRAINAGE

Drainage is essential for maintaining the installation's durability and reducing efflorescence, and subgrade softening. Australian Standards specify that there must be a minimum surface cross-fall to adequate drainage sites.

To discuss suitable drainage systems for your project, please get in touch with your installer.

SCREED AND BONDING SLURRY

Where a screed bed will be installed, permit the concreted base to cure for the time recommended by the manufacturer. An approved cement-based slurry finish must be used to bond the screed to the concrete substrate.

The relevant Australian Standards and manufacturer requirements must be followed while creating sand mixtures and applying them.

WATERPROOFING

Prior to installation, drainage design and waterproofing should be considered as part of a larger "moisture management strategy." Prior to installing the tiles, we advise covering the substrate (preferably the bedding screed) with a waterproofing product or membrane to help prevent efflorescence and other moisture-related problems.

SEALING

It is evident to seal Pool Coping products. Sealing increases the stone's durability and maintains the aesthetics of the stone for a longer time. Stone Centre recommends dip-sealing our Pool Coping before installation. Make sure that the pre-sealing product you use is compatible with the tile adhesive you've chosen.

There is continuous research and development of sealers and there are many sealing products available in the market. We recommend contacting your installer to select the best sealer for Pool Coping.

WEATHER CONSIDERATION

If you are expecting rain or expecting bad weather, avoid installing the Pool Coping.

When laying stones, on hot days (over 30°C), might lead to delamination problems between the stone and the adhesive bedding layer.

CUTTING

Cutting should ideally be done with a bench saw equipped with a wet diamond blade. To prevent cutting paste from drying and damaging the stone's surface, it should be cleansed as soon as it is cut.

Crystalline Silica (Silica dust) is a typical mineral present in soil, sand and stone. Additionally, it is used in the production of materials including bricks, tiles, concrete, and faux stone. When using power tools to cut, grind, and drill such materials, safety gear should be worn because exposure to silica can result in several health problems. On the job site, the correct safety precautions for silica exposure should be followed.

SELECTION OF ADHESIVES FOR BEDDING TILES

To bed stone tiles, we advise using synthetic tile adhesives. Adhesive development and research are always progressing. There are numerous trustworthy businesses and a vast selection of products. Fast-setting tile adhesives should be used in certain conditions.

GROUTING COMPOUND

It is advised to use a premium pre-bagged grouting product that is appropriate for the task.

CONSIDERATIONS FOR GROUTING

Use a sponge to wet the grout joints and the stone.

Place grout into joints to the full depth of the paving stones, making sure there are no voids.

Use a trowel to remove any extra grout.

You can use a water-sponge to clean the paving surface, to remove all the extra grout.

LAYING

Run string lines around the outside of the pool to check for height level and straightness; allow for a mortar bed of around 20mm.

A fluid mixture of an acrylic-based bonding agent needs to be painted onto the fiberglass/concrete "beam."

Application of 3 beds of a medium elastomeric joint sealant/adhesive is recommended on fiberglass pools. Apply no mortar mixture to the fibreglass. Only the concrete beam needs to be covered with mortar mixture.

Mix 3 parts plasterers' sand to 1 part cement and 1 part sand mix with clean water to a cake mixture consistency. In accordance with the manufacturer's directions, add a liquid "waterproofer," then place a bed over the pool beam.

The base of the pool coping piece should be painted with the bonding agent.

Sprinkle 50:50 (Powder Form) of a flexible and waterproof pool tile adhesive and cement to the bed.

Spray the powdered mortar bed with two handfuls of water.

The pool coping should be laid evenly before being levelled. The typical overhang is 30 mm.

Some of the mortar will fall into the pool as it is crushed out. To check for "holes," run your thumb along the joint.

Use a sponge to clean everything consistently. You'll wash the cement out of the sand if you wipe the mortar.

A wide joint of flexible grout should be used to fill the gap between the copers.

FURTHER INSTRUCTIONS

Due to the manufacturing process used to create the product and movement issues specific to a fibreglass shell, Stone Centre does not advise utilising laminated epoxy rebated copings on fibreglass pools; nevertheless, one/full piece rebates of 30mm thickness or above are ideal for this application.

PREPARING BOND BEAM

FIBREGLASS POOL SHELL

Sand the top of the fibreglass pool shell with wet and dry sandpaper to scratch the surface layer and wipe it clean of any dust or residue to improve the sealant's adhesion.

CONCRETE POOL SHELL

To level the horizontal surface over the concrete bond beam, a screed can be needed. Prior to starting installation when the screed procedure has been used, the concrete and screed must cure for time specified by the manufacturer.

MOVEMENT JOINTS

Every corner (internal and exterior), the full rear perimeter of the coping, and movement joints (min 3mm) should all be completed at a maximum of 2.4Lm.

INTERNAL MOVEMENT JOINTS

Between the internal underside of the coping and the internal surface finish, a movement joint (minimum 3mm) should be used. Filling the movement joint should be done with the proper silicone or sealant. In turn, this seals the coping's interior underside and acts as a barrier to stop pool water from entering the space beneath the coping.

ANTI-SLIP TREATMENT

Depending on where your tiles are being installed and other site factors, you should think about anti-slip solutions. If you need advice on the anti-slip treatment, please contact your installer.

CLEANING

Once the grouting substance has dried, clean the stone. Any grouting residue can be removed through cleaning. Sweep any extra dirt off the surface.

Apply a pH-neutral cleanser liberally and in manageable areas to the surface.

Gently scrub the surface with a nylon pad (such as Doodlebug from 3M) or a stiff broom.

Use a wet-vac or squeegee to remove any residue from the surface.

To get the finest results, hiring a professional cleaner and sealer may be appropriate. It is important not to use any acidic cleaners.

POST INSTALLATION SEALING

For preserving the durability and aesthetic appeal of Pool Coping, Stone Centre suggests post-installation sealing. Always carefully adhere to manufacturer directions to get the best results for the stone's appearance and protection. Please contact your installer for further details on the best sealing recommendations.

POST INSTALLATION MAINTENANCE

Over time, Pool Coping will need some sort of upkeep, which will vary from surface to surface and be greatly influenced by use, location, and product type. Cleaning alone or a combination of cleaning and sealing may be required depending on the product type and maintenance requirements.

ACCEPTABLE CHARACTERISTICS

Stone Centre's Pool Coping are made from naturally occurring material, therefore there may be variations in colour and/or surface finish. You might also notice a fossilised texture on some of the Pool Copings we supply. It is important to note this fossilised texture is not a defect, but it is considered to increase the beauty of your project post installation. The user oversees inspecting the tiles before laying them. Small scratches and chips are not flaws because they are not structurally sound. A warranty claim may be made for any tile that exhibits significant chipping or variation in thickness and dimension before installation.

Please Note: Pool Coping may fade a little over time when fully exposed to UV in outdoor conditions.

STONE CENTRE

SYDNEY | MELBOURNE | BRISBANE | ADELAIDE

1300 989452 | www.stonecentre.com.au